



# AGGLO™

Porcelain Tile




[www.everstone.com.au](http://www.everstone.com.au)



AGGLO™ Porcelain Tile



### MURANO




1200x600 Graphic Patterns



**AGGLO™** Porcelain Tile



**LIDO**




1200x600 Graphic Patterns

AGGLO™ Porcelain Tile



**RIALTO**




1200x600 Graphic Patterns

AGGLO™ Porcelain Tile




**TORCELLO**




1200x600 Graphic Patterns


**LIDO**




**MURANO**




**TORCELLO**




**RIALTO**



Available sizes :



1200x600



600x600



600x300

≧ 10MM

Matt Finish

Name	Product Code	Nominal Size	Finish	Faces	Pc/Box
Agglo Lido	GP-AGG-LID12060M	1200x600	Matt	4	2
Agglo Lido	GP-AGG-LID6060M	600x600	Matt	8	4
Agglo Lido	GP-AGG-LID6030M	600x300	Matt	16	6
Agglo Murano	GP-AGG-MUR12060M	1200x600	Matt	4	2
Agglo Murano	GP-AGG-MUR6060M	600x600	Matt	8	4
Agglo Murano	GP-AGG-MUR6030M	600x300	Matt	16	6
Agglo Rialto	GP-AGG-RIA12060M	1200x600	Matt	4	2
Agglo Rialto	GP-AGG-RIA6060M	600x600	Matt	8	4
Agglo Rialto	GP-AGG-RIA6030M	600x300	Matt	16	6
Agglo Torcello	GP-AGG-TOR12060M	1200x600	Matt	4	2
Agglo Torcello	GP-AGG-TOR6060M	600x600	Matt	8	4
Agglo Torcello	GP-AGG-TOR6030M	600x300	Matt	16	6

TECHNICAL SPECIFICATIONS			RECOMMENDED APPLICATIONS	
Water Absorption (ISO10545-3)	≤ 0.5% (Result 0.06%)	Chemical Resistance (ISO10545-13)	PASS (A-LA-HA)	Exterior Wall <input checked="" type="checkbox"/>
Breaking Strength (ISO10545-4)	PASS ≥ 1300 N	Stain Resistance (ISO10545-14)	PASS Class 5	Interior Wall <input checked="" type="checkbox"/>
Modulus of Rupture (ISO10545-4)	PASS ≥ 35 N/MM <sup>2</sup>	Slip Resistance (AS/NZS 4586 Appendix A, D)	<b>Matt Finish</b>	Residential Floor <input checked="" type="checkbox"/>
Abrasion Resistance (ISO10545-7)	CLASS 4	▪ Oil Ramp	R10	Commercial Floor # <input checked="" type="checkbox"/>
Frost Resistance (ISO10545-12)	PASS	▪ Wet pendulum	P3	Shade Variation <input type="checkbox"/> V3

# Subject to local slip resistance regulations for area of use or as recommended by Standard Australia guide HB 198:2014